

Property

Product	PEG-300
----------------	---------

General Information

Key Features

- Low Dioxane content
- Low Free-EO content

Applications

- Rubber, Resins, Cellulosic materials, Dispersants, Textile and leather, Printing inks

Item	Measuring Method	Unit	Value
Physical Properties			
Molecular weight	LC METHOD	-	285-315
Appearance (25°C)	VISUAL	-	Liquid
Color (50°C)	ASTM D5386	APHA	Max 30
pH	LC Method	-	5.0-7.0
Hydroxyl Value	LC Method	mgKOH/g	356.0-394.0
Water contents	ASTM E 203	wt%	Max 0.10
Viscosity (50°C)	ASTM D2196	cP	66.0-72.0

1. Physical Properties : these are not to be construed as specifications
2. ISO 9001, 14001, /TS 16949

* The last update date : 2026/06/01